

## **COLORPRINT PU**

### **Description**

PU heat seal material with polyester backing, created for inkjet digital printing & cutting systems with solvent or eco solvent based inks.

Average thickness: 80 micron

### **Basic information**

Due to the many different base materials available on the market, the following heat transfer instructions are given as guideline only:

**Plotter settings** (eg. with ROLAND VP-300 plotter)

**Blade:** new at 50° **Minimum required pressure:** 50 gf

**Transfer setup**

**Temperature:** 165°C **Time:** 20" **Pressure:** medium (3÷4 bar)

### **Application instructions**

- 1) Print and cut the material
- 2) Weed the exceeding material
- 3) Remove the print from the polyester backing using Siser's T.T.D. Easy (adhesive, transparent and resistant to high temperatures)
- 4) Heat apply
- 5) Remove the application tape warm (should you use other application tapes, follow the manufacturer's instructions)

### **Suitable textiles**

Cotton, polyester and blends of these materials (not suited for treated and dye sublimation fabrics)

### **Washing instructions**

(wait 24h after the heat transfer) 60°C max. – inside out – do not use bleach or other aggressive chemical agents

**Dry clean:** no **Tumble dry:** not recommended

*N.B. : all information given in this sheet are based on our experience*

**We recommend to always perform a test before starting standard production**

The product meets the Italian and EU regulations relating to its proper use.

This document can be subject to variations. Updated versions are available on our website [www.siser.it](http://www.siser.it).

For further information, please contact our Sales Office. Thank you.

### **SISER s.r.l.**

V.LE DELLA TECNICA n. 18 – 36100 VICENZA ITALY

TEL. +39 0444 287960 - FAX +39 0444 287959 - E-mail: [info@siser.it](mailto:info@siser.it) - [www.siser.it](http://www.siser.it)

R.E.A. VI 171856 VI – Reg. Imp. VI n. 14971 - Cap. Soc. € 103.300 i.v. – Partita IVA 01591490246



Organizzazione con sistema di gestione certificato  
ISO 9001:2008